

COLLOIDAL SELF ASSEMBLY II: PACMEN & MULTIVALENT COLLOIDS

David Pine
Department of Physics
New York University

2012 Boulder Summer School


25 July 2012
Boulder, Colorado

Outline of lectures on colloids

- Lecture I: Yesterday
 - ▶ Overview of colloids (sizes, materials)
 - ▶ Self-assembly of colloids: (colloidal liquids, crystals, & glasses)
 - photonic crystals (& the diamond lattice)
 - need for directional interactions
 - ▶ van der Waals interactions (fluctuating electric dipoles)
 - ▶ Electrostatic interaction: Poisson-Boltzmann & Debye-Hückel, DLVO
 - ▶ Depletion interaction
 - ▶ DNA hybridization
- Lecture II: Today
 - ▶ Lock & key colloids
 - ▶ Colloids with valence
 - ▶ Colloidal molecules: to infinity and beyond



Lock & Key Colloids

Drawing inspiration from proteins ...




Pac-Man Particles

Lock & Key Colloids




Pacman particle synthesis

TPM =



Water


Oil



o/w emulsion




Shake



Oil = "TPM" = 3-methacryloxypropyl trimethoxysilane


Make emulsion
(oil droplets in water)

Pacman particle synthesis



Water


Oil



o/w emulsion





Shake



Oligomerize oil

◆ Oligomerize Si-O groups (pH \uparrow) N~1-10



Pacman particle synthesis



Polymerize shell

- ◆ Oligomerize Si-O groups (pH \uparrow) N~1-10
- ◆ Polymerize methacrylate groups (free radical)
 - Creates porous shell
 - Nucleates TPM nanoparticles in solution outside of TPM droplets

Pacman particle synthesis




Polymerize shell

- ◆ Oligomerize Si-O groups (pH \uparrow) $N \sim 1-10$
- ◆ Polymerize methacrylate groups (free radical)
 - Creates porous shell
 - Nucleates TPM nanoparticles in solution outside of TPM droplets
 - Osmotic imbalance sucks small oligomers out of TPM droplets (through shell)


And ...

Pacman particle synthesis



Water


Oil



o/w emulsion





Shake





Shell buckles


Pacman particles







Pacman particles



$$d_l = 1.5 - 3.5 \mu\text{m}$$




Monodisperse pacman particles



Pacman lock & key

$$S \sim n_{\text{poly}} \ln V$$

depletion zones




non adsorbing
polymer


Pacman lock & key

$$S \sim n_{\text{poly}} \ln V$$

depletion zones




non adsorbing polymer



Max overlapping volume


can tune interaction strength



key too small


$$\Delta S \sim n_{\text{poly}} \frac{\Delta V}{V}$$

Pacman depletion movie




Watch this pac-man


Particle (key) binds to
PacMan (lock)





Size selectivity



Pacman depletion movie




Watch this pac-man




Sacanna et al., Nature **464**, 575–578 (2010)


Colloidal couplings




Monomer



Dimer



Trimer



Lock-and-key binding model

$\mathcal{L} + \mathcal{K} \rightleftharpoons \mathcal{LK}$ chemical equilibrium between locks & keys

$\mu_L + \mu_K = \mu_{LK} \Rightarrow \frac{n_{LK} n_0}{n_L n_K} = e^{-[E_b + k_B T \ln(V_b n_0)]/k_B T}$


$k_B T \ln \frac{V_b}{v_u}$

binding energy

binding volume (entropy)

$E_b = -k_B T n A (2r_p - r_0 - \kappa^{-1})$

overlap area
 polymer (depletant) radius
 equilibrium separation
 Debye screening length (repulsion)




Lock & key binding energy: balance between electrostatic repulsion and depletion attraction

Entropy: binding volume vs unbound volume per key

Lock-and-key binding data

$$\mu_L + \mu_K = \mu_{LK} \quad \Rightarrow \quad \frac{n_{LK} n_0}{n_L n_K} = e^{-[E_b + k_b T \ln(V_b n_0)]/k_B T}$$










fitting parameters

$$A \approx 0.5 \mu\text{m}^2$$

$$\approx 1/15^{\text{th}} A_{\text{sphere}}$$

$$V_b \approx 0.005 \mu\text{m}^3$$


Pacman polymers




Tunable depletion attraction

$$\Delta S \sim n_p \frac{\Delta V}{V}$$

NIPAM gel particles shrink when heated above 39°




$T \approx 25^\circ$



$T \approx 40^\circ$

Melting


Start at 25°C, then heat to 40°C




Particle pairs dissociate at 40°C

Towards a more perfect pacman

Heterogeneous nucleation




Cartoon





The real colloids


seeds




TPM on seeds



old pacmen



pacmen




Lock & key interaction


$$\mu_L + \mu_K = \mu_{LK} \quad \Rightarrow \quad \frac{n_{LK} n_0}{n_L n_K} = e^{-[E_b + k_B T \ln(V_b n_0)]/k_B T}$$

binding energy binding volume (entropy)


old pacmen



pacmen




Self-replicating pacmen



Colloids with directional bonds

How can we make colloids with multiple direction bonds?



CO₂




CH₄



SO₂


Start by assembling colloids in a controlled way ...

How to make colloidal clusters




Emulsion pictures

particle-in-oil in
water emulsion




swollen particle bound
to droplet interface




toluene droplet

Emulsion & cluster pictures

particle-in-oil in
water emulsion




swollen particle bound
to droplet interface



toluene droplet

clusters after
removal of oil





solid particle
cluster




Cluster formation

particles are confined to droplet surface, not the interior



capillary force pulls spheres towards center




|| first minimal moment clusters

$$M_2 = \sum_0^n (\mathbf{r} - \mathbf{r}_{cm})^2$$



John Conway*
(Princeton)




* Conway, Sloane, et al.
Discrete Comp. Geom.
14, 237 (1995)

Assembled by John Conway, Neil Sloane et al.

Manoharan et al.
Science **301**, 483 (2003)

Separating clusters



$$\Delta mg = 6\pi\eta R_{hyd} v_{sed}$$

$$\Rightarrow v_{sed} = \frac{\Delta\rho}{\eta} R_{hyd}^2 g$$

It's a race


Clusters with large hydrodynamic radius sediment faster

$$\Delta mg = 6\pi\eta R_{hyd} v_{sed}$$


$$\Rightarrow v_{sed} = \frac{\Delta\rho}{\eta} R_{hyd}^2 g$$

It's a race


Clusters with large hydrodynamic radius sediment faster





Making patchy particles



amidinated
PS spheres





cluster




swell cluster with
styrene (emulsion)


polymerize
styrene




amidinated
patchy sphere





swell with
styrene





Patchy particles



amidinated
PS spheres




cluster




swell cluster with
styrene (emulsion)

polymerize
styrene




amidinated
patchy sphere


clusters




patches





Functionalizing patchy particles



amidinated PS spheres





cluster



swell cluster with styrene (emulsion)


polymerize
styrene



amidinated patchy sphere



NHS biotin





biotinated patchy particle

fluorescent streptavidin




streptavidin-biotin with sticky DNA





Functionalizing patchy particles

patches




fluorescent




Purified patchy particles


2 patches



3 patches



Linking up: it's specific!



AB

AB₂

AB₃


AB₄

Alternating
copolymer/oligomer

scale bar = 800 nm

Colloidal molecules


small patches



AB_4 formation kinetics




Colloidal polymerization kinetics




Divalent particle polymerization kinetics

Controlling patch size



Linking with
complementary
particles



big patches

Collaborators

Stefano Sacanna
NYU




Gi-Ra Yi
Sungkyunkwan University (S. Korea)

Laura Rossi
Utrecht University



William Irvine
NYU/University of Chicago

Paul Chaikin
NYU




Marcus Weck
NYU

Yu Wang
NYU



Yufeng Wang
NYU

Dana Breed
UCSB/NYU/Dow



Vinny Manoharan
UCSB/Harvard

Pacmen

Colloidal
Molecules



W. M. Keck Foundation

